

## TEST METHODS AND RESULTS

Nr.	Characteristics of verifications	Unity of measure	Methods	Results
1	Moisture	%	DIN 51718	7,04
2	Ash	%	DIN 51719	0,5
3	Calorific value,Q	kJ/kg MWh/tonn	ISO 1928	18255 5,07
4	Density	g/cm3	DIN 52182	1,16
5	Bulk density	kg/m3	SS 187178	681,2
6	Sulphur content	%	ISO 334	0,01
7	Mechanical strength <small>(loss due to crumble off)</small>	%	SS 187180	2,42

Ltd. "Ecosource"